

IN THE SPECIFICATION:

Please rewrite paragraph [0052] to read as follows:

--Referring to Figures 4(c)-(d), a single low energy implant (~~please enter the energy of the implant~~) is introduced via ion implantation to form a dopant region 20 including deep source/drain regions and shallow source/drain extensions [[20]]. Implant energies for forming the dopant region 20 include ranges similar for forming source/drain regions ~~are;~~ typical[ly;]] ranges are from about 1 keV to about 5 keV, preferably about 3 keV, for arsenic; from about 1 keV to about 7 keV, preferably about 4 keV, for BF₂; and from 1 keV to about 2 keV, preferably about 1 keV, for boron. Following the single low energy implant, an activation anneal is conducted at approximately 850°C, more preferably at about 1000°C as depicted in Figure 3(d). Although boron is preferred, other types of Group III elements may be utilized for producing PFET devices. --

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☒ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.